

## Technical Data

3550 West Market Street Akron, Ohio 44333 Phone 1-800-54-RESIN Fax 1-800-662-7203  
CORPORATE OFFICE  
www.aschulman.com • info@aschulman.com



# POLYAXIS PD 2000

NATURAL/COLORS/BLACK

**Polyaxis PD 2000 is a polypropylene specifically designed for rotational molding. Improved room temperature impact and ease of molding are two of the most important traits that make this resin an excellent choice for applications requiring the characteristics of polypropylene.**

RESIN PROPERTIES	TEST METHOD	TEST PARAMETERS	UNIT	TYPICAL VALUE
Melt index	ASTM D-1238	2.16/230	g/10 min	17
Density	ASTM D-792	-----	g/cc	.9

### TYPICAL PHYSICAL PROPERTIES

Tensile Strength	ASTM D-638	@ yield, 2"/minute	Mpa psi	25.9 3760
Ultimate Elongation	ASTM D-638	2"/minutes	%	30
ESCR	ASTM D-1693	100% Igepal	hours F50	>1000
Flexural Modulus	ASTM D-790	@ 1% Secant	Mpa psi	1288.4 187,000
Heat Distortion	ASTM D-648	@ 66 psi	°C	120
Impact	ARM	(23°C) 1/8" Specimen	ft - lbs.	14

09/01



Values listed are typical properties and should not be used as specification limits. Physical properties are based on rotationally molded samples from unpigmented resin. Procedures may have been modified to accommodate laboratory capabilities. Density and ESCR tests were performed on compression molded samples.

While the information herein is believed to be reliable and correct, nothing herein is intended and should not be construed as a representation of warranty, express or implied, as to results obtained or to be obtained by others who may make use of this information or with respect to the absence, existence or validity of patent rights, if any, of others involving any composition or process herein referred to; or an inducement or recommendation for the violation of any such patent rights; and responsibility and liability therefore is disclaimed.