

Technical Data

3550 West Market Street Akron, Ohio 44333 Phone 1-800-54-RESIN Fax 1-800-662-7203
www.aschulman.com • info@aschulman.com

CORPORATE OFFICE



A. Schulman
COMPOUNDING YOUR SUCCESS™

Schulaflex SF 302

NATURAL/COLORS/BLACK

Schulaflex SF 302 is an ethylene-based butene plastomer.
Available in natural as a non-UV stable product, it can be compounded as natural or colors
with a full UV package. It is ideally suited for products requiring a soft feel.

RESIN PROPERTIES	TEST METHOD	TEST PARAMETERS	UNIT	TYPICAL VALUE
Melt index	ASTM D-1238	2.16/190	g/10 min	9
Density	ASTM D-792	-----	g/cc	.905
Hardness	ASTM D-2240	Shore A	15 sec	38

TYPICAL PHYSICAL PROPERTIES

Tensile Strength	ASTM D-638	yield,2"/minute	Mpa Psi	7 1,000
Ultimate Elongation	ASTM D-638	2"/minute	%	820
ESCR	ASTM D-1693	100% Igepal	hours F50	>1000

09/01



MEMBER

Values listed are typical properties and should not be used as specification limits. Physical properties are based on rotationally molded samples from unpigmented resin. Test procedures may have been modified to accommodate laboratory capabilities. Density and ESCR tests were performed on compression molded samples.

While the information herein is believed to be reliable and correct, nothing herein is intended and should not be construed as a representation of warranty, express or implied, as to results obtained or to be obtained by others who may make use of this information or with respect to the absence, existence or validity of patent rights, if any, of others involving any composition or process herein referred to; or an inducement or recommendation for the violation of any such patent rights; and responsibility and liability therefore is disclaimed.